

Saragossa - short	
Description	2 back pockets, one of them with flap, pen pocket, hammer loop, left side pocket with flap, rule pocket, adjustable waist, YKK® zip.
	
Maintenance	<p>Maximum wash temperature: 60°C; Do not bleach; Dry clean with solvents on point F plus Tetrachloroethylene; Do not dry in a tumble dryer; Ironing at low temperature (max 110 °C).</p> <div style="display: flex; justify-content: space-around; align-items: center;">      </div>
Item	<p>V057-0-00 khaki/black V057-0-01 navy V057-0-02 royal blue/black V057-0-03 clay brown/black V057-0-04 anthracite/black V057-0-05 black/black</p>
Standards	<p>EN ISO 13688:2013</p> <div style="text-align: right;">  </div>
sizes	44 – 64

SAFETY TECHNICAL SPECIFICATIONS

Test method	description	Cofra result	minimum requirement / range	
Background fabric	EN ISO 1833-1977, SECTION 10	Composition: cotton canvas Weave: Canvas plain 1/1	100% Warp: 8+8 [yarn/cm] Weft: 5+5 [yarn/cm]	
	EN ISO 12127:1996	Weight per unit area	257 g/sqm	
	EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change: 4 – 5	1 - 5
	ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	warp: - 2.6 % weft: - 0.5 %	Max ± 3 % Max ± 3 %
	ISO 105X12: 2001	Colour fastness to rubbing	dry: 4 - 5 wet: 4 - 5	1 - 5 1 - 5
	EN ISO 105 B02: 1993, Method 3	Colour fastness to light	4	1 - 5
	ISO 105-N01:1993	Colour fastness to bleaching	Colour change: 4	1 – 5

EN ISO 13934-2: 1999	Tensile strength	warp: 500 N weft: 410 N	400 N 400 N
EN ISO 13688:2013 paragraph 4.2 (EN 1413)	The pH's determination from the watery extract	8.9	3,5<PH≤9,5
EN ISO 13688:2013 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm